

PRINTEX[®] kappa 10

Product Information

0523

Physico-chemical properties

Parameter	Method	Unit	Value
OAN	following ASTM D 2414	ml/100g	145
BET	following ASTM D 6556	m ² /g	74
pH	following ASTM D 1512		8
Ash content	following ASTM D 1506	%	0.01
Heating loss 125°C	following ASTM D 1509	ppm	2000
Sieve residue 45 µm	following ASTM D 1514	ppm	5
Iron content	following Orion method	ppm	10
Zn, Cu, Co, Ni, Cr, Mn	following Orion method	ppm	sum 10

1. General description

- Furnace Black
- Regular Color Furnace Type (RCF)
- Colour Index generic name: Pigment Black 7
- Colour Index constitution No.: 77266

2. Chemical description

Industrially produced Specialty Carbon Black.

3. Application

High-voltage cable and batteries

4. Fastness properties

Light Fastness Mass Tone ISO105, B01	8
Color Index	#7

5. Forms of supply

Available in 15 kg PE-bags on 600 kg pallets or in 800 kg FIBCs

6. Storage stability

The high surface area of Specialty Carbon Blacks bears the inherent risk of adsorption of vapors and/or gases, which in turn impacts the product's application relevant properties. It is therefore recommended to always store Specialty Carbon Blacks out of reach of potential contaminants and sources of contamination. Storage temperatures should not exceed 50°C.

Carbon black should be stored under cool and dry conditions. Please refer to our product safety data sheet. Densification or adsorption processes etc. may adversely affect the product's application relevant properties. This also applies to storage in silos or other closed containers.

7. Technical literature

Technical literature on the use of Specialty Carbon Blacks can be ordered at the below mentioned address.



The Americas

Orion Engineered Carbons LLC
4501 Magnolia Cove Drive, Suite 106
Houston, TX 77345
USA
Phone +1 832 445 3300

AMERICAS@orioncarbons.com

Europe/ Middle East/ Africa

Orion Engineered Carbons GmbH
Hahnstraße 49
60528 Frankfurt am Main
Germany
Phone +49 69 36 50 54 100

EMEA@orioncarbons.com

Asia Pacific

Orion Engineered Carbons (China) Investment Co., Ltd.
Room 3701-3702, BM InterContinental Business Center,
100 Yutong Road
Shanghai 200070, P. R. China
Phone +86 21 61 07 09 66

APAC@orioncarbons.com

Incorporated in Luxembourg

Orion Engineered Carbons S.A., 6 Route de Trèves, L-2633 Senningerberg, Luxembourg, Phone +352 27 04 80 60

www.orioncarbons.com

All statements given by Orion Engineered Carbons GmbH as well as its affiliates, including for example Orion Engineered Carbons S.A. ("Orion") herein are provided for information purposes only and are given as of the date of this document and are based on the knowledge on the date of the document. ORION DOES NOT GIVE ANY REPRESENTATION OR WARRANTY THAT THE CONTENTS OF THE GIVEN STATEMENTS AND INFORMATION ARE CORRECT OR ACCURATE. ANY LIABILITY OF ORION WITH REGARD TO THE CONTENTS PROVIDED ARE HEREBY EXPRESSLY EXCLUDED. Orion does not give a warranty with respect to any results to be obtained from such information, any uses of such information or with regard to the non-infringement of any proprietary right. Nothing stated herein shall be construed as a license of or recommendation for use, especially with concern to the potential infringement of any proprietary right. Use or application of such information or statements or the material or systems described herein are at user's sole discretion and risk. The user acknowledges that Orion shall bear no responsibility or liability for any use or application of such information or statements or the material or systems described herein. All sales are subject to the respective standard terms and conditions of Sale issued by Orion including but not limited to the limitation of liability contained therein. The Orion standard terms and conditions of Sale can be reviewed, downloaded and printed under https://orioncarbons.com/en/general_conditions_of_sale_and_delivery_orion_engineered_carbons_europe_africa.pdf. Any and all information disclosed by Orion herein shall remain the property of Orion.

© 2021 Orion Engineered Carbons GmbH

OEC-PI 0523-07/2017