

LAMP BLACK 101

Product Information

0554

Physico-Chemical Properties

Parameter	Method	Unit	Value
OAN Oil Absorption Number	following ASTM D 2414	ml /100 g	140
BET Surface Area	following ASTM D 6556	m ² /g	29
pH	following ASTM D 1512		8
Sieve Residue 45µ	following ISO 787-18	ppm	<100
Ash Content	following ASTM D 1506	%	0.02

1. General Description

- Lamp Black
- Color Index generic name: Pigment Black 6
- Color Index constitution No.: 77266

2. Chemical Description

Industrially produced Specialty Carbon Black

3. Application

Polymers, Printing Ink, Coatings, Batteries & Special Applications

4. Impurity Levels

Parameter	Unit	Value
Cadmium	ppm	1
Chromium	ppm	1
Copper	ppm	1
Iron	ppm	5
Manganese	ppm	1
Mercury	ppm	1
Nickel	ppm	1
Tungsten	ppm	2

Those values are typical impurity levels that can be expected. They are not part of any specification.

5. Forms of Supply

Beads and Powder, available in 25 kg paper bags and 500 kg FIBC

6. Regulation

Complies with Commission Regulation (EU) No. 10/2011 on "plastic materials and articles intended to come into contact with food" (14.01.2011) and amendments; Annex I, additive specification for FCM substance No. 411, Ref. No. 42080.

7. Storage Conditions

The high surface area of Specialty Carbon Blacks bears the inherent risk of adsorption of vapors and/or gases, which in turn impacts the product's application relevant properties. It is therefore recommended to always store Specialty Carbon Blacks out of reach of potential contaminants and sources of contamination. Storage temperatures should not exceed 50 °C.

Carbon Black should be stored under cool and dry conditions. Please refer to our Product Safety Data Sheet. Densification or adsorption processes etc. may adversely affect the product's application relevant properties. This also applies to storage in silos or other closed containers.

8. Technical Literature

Technical literature on the use of Specialty Carbon Blacks can be ordered at the below mentioned address.



The Americas

Orion Engineered Carbons LLC
4501 Magnolia Cove Drive, Suite 106
Kingwood, TX 77345
USA
Phone +1 832 445 3300

AMERICAS@orioncarbons.com

Europe/ Middle East/ Africa

Orion Engineered Carbons GmbH
Hahnstraße 49
60528 Frankfurt am Main
Germany
Phone +49 69 36 50 54 100

EMEA@orioncarbons.com

Asia Pacific

Orion Engineered Carbons Trading (Shanghai) Co., Ltd.
BM Intercontinental Business Centre, Room 3701-3702
100 Yutong Road
200070 Shanghai, China
Phone +86 21 6107 0966

APAC@orioncarbons.com

Global Corporate Headquarters

Orion Engineered Carbons S.A., 6 Route de Trèves, L-2633 Senningerberg, Luxembourg, Phone +352 27 04 80 60

www.orioncarbons.com

All information and statements contained herein are believed to be accurate, however Orion Engineered Carbons GmbH (as well as all other Orion Engineered Carbons group companies including Orion Engineered Carbons SA), its agents and/or affiliates give no warranty with respect thereto, including but not limited to any results to be obtained or the non-infringement of any proprietary right. Use or application of such information or statements or the material or systems described herein is at user's sole discretion and risk, and consequently user acknowledges that Orion Engineered Carbons GmbH (as well as all other Orion Engineered Carbons group companies including Orion Engineered Carbons SA), its agents and/or affiliates shall bear no responsibility or liability for same. Nothing herein shall be construed as a license of or recommendation for use, especially with concern to the potential infringement of any proprietary right. All sales are subject to the respective Standard Terms & Conditions of Sale issued by Orion Engineered Carbons GmbH or - as the case may be - another Orion Engineered Carbons group company, including but not limited to the Limited Warranty clauses contained therein.

© 2018 Orion Engineered Carbons GmbH

OEC-PI 0554-08/2018